




HP Professional Instant-dry Satin Photo Paper, 3-in Core



The HP Designjet printing system—the complete solution

HP Designjet printers, Original HP inks and printheads, and Original HP printing materials are designed to work together as a system to provide reliable, consistent results with every print.



See long-lasting, exhibition-ready photographs

Produce exhibition-ready photographs

See vivid color, sharp detail, and striking contrast. It's easy to handle large-size exhibition prints on this durable, professional-grade weight paper that offers the look and feel of a professional photo paper.

Provide long-lasting results

Deliver your photographs with reassurance. Designed together with HP pigment inks, prints produced on HP Professional Instant-dry Satin Photo Paper resist fading indoors, away from direct sun for up to 200 years.¹

See reliable results, consistent performance

Experience the reliable performance of the HP Designjet large format printing system. HP Professional Instant-dry Satin Photo Paper, 3-in Core is engineered with Original HP inks and the printer to deliver consistent image quality and excellent handling.

¹ With Original HP 91 or HP 70 Photo Inks. Display permanence rating for interior displays/away from direct sunlight, under glass by HP Image Permanence Lab and/or by Wilhelm Imaging Research, Inc. on a range of HP media. For more information, see globalBMG.com/hp/t/printpermanence.

² With Original HP 91 or HP 70 Photo Inks. Performance varies based on printer and print profile. Water resistance testing by HP Image Permanence Lab on a range of HP media and follows ISO 18935 method. For more information, see globalBMG.com/hp/t/printpermanence.

Target customers	Applications	Benefits
Professional photographers	Photo enlargements	Professional, satin surface for impressive image depth and clarity at any angle
Fine artists	Art reproductions	Heavy weight makes large-size, exhibition prints easy to handle
Graphics-oriented print service providers		Consistent gloss uniformity
		Up to 200 years display permanence with Original HP pigment inks ¹
		Water resistant prints ²
		Handle instant-dry prints right off the printer

Technical specifications



HP Professional Instant-dry Satin Photo Paper, 3-in Core

For the latest ICC profiles/paper presets and a variety of resources to help you get the most out of your printer and HP large format printing materials, please visit globalBMG.com/hp/.

Weight	300 g/m ² per ISO 536 Test Method			
Thickness	287 microns/11.3 mil per ISO 534 Test Method			
Opacity	Greater than 97% per TAPPI T-425 Test Method, greater than 95% per ISO 2471 Test Method			
Brightness	Greater than 91% per TAPPI T-452 and ISO 2470 Test Methods			
Whiteness	Greater than 115 per CIE Ganz 82 Test Method			
Finish	Satin			
Operating temperature	15 to 35° C / 59 to 95° F			
Operating humidity	30 to 80% RH			
Display permanence (Indoor home or office)	Up to 200 years with Original HP 91 or HP 70 Photo Inks ³			
Water resistance	Water resistant with Original HP 91 or HP 70 Photo Inks ⁴			
Dry time	Quick dry (at 23° C, 50% RH)			
Lamination	Yes, hot or cold with commercially available pressure-sensitive and thermal laminate films			
Shelf life	Greater than 1 year, unopened in original packaging			
Storage temperature	0 to 40° C / 32 to 104° F			
Storage humidity	25 to 80% RH			
Country of origin	Product of Germany			
Ordering information	Product numbers	Roll sizes	UPC codes	Region
	Q8759A	610 mm x 15,2 m (24 in x 50 ft)	848412013542	Worldwide
	Q8840A	1118 mm x 15,2 m (44 in x 50 ft)	848412013559	Worldwide
Warranty	HP large format printing materials are free from defects in materials and workmanship. For warranty statement, please see globalBMG.com/hp/MediaWarranties .			

³ Display permanence rating for interior displays/away from direct sunlight, under glass by HP Image Permanence Lab and/or by Wilhelm Imaging Research, Inc. on a range of HP media. For more information, see globalBMG.com/hp/t/printpermanence.

⁴ Performance varies based on printer and print profile. Water resistance testing by HP Image Permanence Lab on a range of HP media and follows ISO 18935 method. For more information, see globalBMG.com/hp/t/printpermanence.

For detailed information on the HP large format print media portfolio and to order, visit globalBMG.com/hp

